



MORGAN MATERIALS

INCORPORATED

380 Vulcan Street Buffalo, New York 14207 USA
Telephone: (716) 873-2000 FAX: (716) 873-2181

Untreated Fumed Silica

Product: 700-D

Chemistry

Tamped Density	125g/l
Surface Area	200m ² /g
Boiling Point	2230 C
Water Solubility	Insoluble
Relative Density	2.2@ 20 C
pH	3.6-4.5
Average Particle Length	0.2-0.3 um

For inquiries or sample requests contact:

Joe Miano 716-873-2000

jmiano@morganmaterials.com