



# MORGAN MATERIALS

INCORPORATED

380 Vulcan Street Buffalo, New York 14207 USA  
Telephone: (716) 873-2000 FAX: (716) 873-2181

## Product Data Sheet

### TR 90 Resin

TR 90 Resin is a thermally stable polyterpene tackifier with light color and moderate softening point. It has a good balance of tack and heat resistance properties and exhibits minimal changes in properties upon exposure to elevated temperatures.

#### PRODUCT PROPERTIES<sup>1</sup>

	<u>Specifications</u>	<u>Typical Analysis</u>
Softening Point, (R&B), °C	86 - 92	89
Color, Gardner (50% in heptane)	4 max.	3
Specific Gravity, 25°/25°C		0.98
Pounds Per Gallon, 25°C		8.2
Flash Point, Closed Cup, °C (°F)		190 (375)

#### SUGGESTED APPLICATION:

- Adhesives and Chewing Gum Base

Contact: Joe Miano at 716-873-2000

[jmiano@morganmaterials.com](mailto:jmiano@morganmaterials.com)